

**ANALYSIS SHEET**

Dated: 27-06-2023

**CALCIUM FLUORIDE**

Sr	Proudct	Grade	Size	SiO2		CaCO3		Capacity/Month
				Typical	Max	Typical	Max	
1	CaF2	75-82%	0-10mm	9%	11%	4%	5%	1000MT
2	CaF2	88%	0-10mm	7%	9%	3%	5%	500MT
3	CaF2	88%	3-10mm	7%	9%	4%	5%	1000MT
4	CaF2	86-90%	6-30mm	5%	7%	3%	5%	1000MT
5	CaF2	86-90%	10-60mm	5%	7%	3%	5%	1000MT
6	CaF2	95-96%	10-50mm	1%	2%	1%	2%	200MT

Sr	Testing Item	Testing Protocol
2	CaF2	Based on ASTM E- 815-17
3	CaCO3	Based on ASTM E-815-17
4	Silica as (SiO2)	Based on ASTM E-1506-08
5	Moisture	Gravimetric

- \* Sizing can be adjusted per requirement
- \* Packing 1MT - 1.2MT Jumbo Bags
- \* For bulk shipments marked packing can be done

**THIS DOCUMENT SHOWS BARE SYNDICATE'S STANDARD SPECIFICATION. UPON REQUEST, MODIFICATION MIGHT BE AVAILABLE.**